


Kerabit 3300 UTL Nature

Päivitetty 25.5.2023 Tulostettu 7.5.2024

The low-carbon status of Kerabit Nature® products is achieved, for example, by replacing some of the traditional raw materials with bio-based raw materials and recycled materials. **The carbon emissions (GWP_{total}) during the manufacture of Kerabit Nature products are approximately 59 % lower than for corresponding basic products.** Apart from environmental impact, the characteristics of the products correspond to the analogous basic products. We are especially careful about the waterproofing properties – we don't compromise on them!

Kerabit 3300 UTL Nature is a line-torch-on underlay membrane in multi-layer membrane system.

The carrier consists of polyester. The underside of the product is coated with torch-applied bitumen, the top surface with sand.



Technical data

| | |
|--|--|
| Manufacturer / Manufactured for | Kerabit Oy, Lohja plant |
| Country of origin | Finland |
| Conformity marking | CE |
| Reaction to fire | Manufacturer's declaration of the fire test |
| Fire Classification | B _{ROOF} (t2) |
| Manufacturer's declaration of conformity | Kerabit modified bitumen roofing |
| Quality control | Quality control carried out at the Plant quality control and a quality control agreement between the Plant and Eurofins Expert Services Oy |
| SFS-labeling | K-TMS 170/3300 torch |
| Product category | TL 2 |
| Nominal thickness | approx. 2,5 mm |
| Nominal weight | 3300 g/m ² |
| Weight of the supportive layer | 170 g/m ² (+/- 10 g/m ²) |
| Supportive layer | polyester |
| Surface type | sand granules |
| Rolls size | 1 x 10 m / 10 m ² |
| Packages / pallet | 24 rll |
| Weight / package | 33 kg |
| Weight / pallet | 817 kg |

Additional information

Kerabit

Handling and storage

Modified bitumen membranes are to be stored on pallets in a dry and cool place. Use a plastic hood or tarpaulin for protection. When the outdoor temperature exceeds +40°C, the rolls must be protected from sunlight.

Applications

This product can be used as an underlayer in multi-layer bitumen roofing or under discontinuous roofing as well as vapour barrier membrane.